



Features

Safety Sealed Packaging (S-XXL) 100 Gloves/Box, 10 Boxes/Case

- Soft and comfortable
- Color: Orange
- 8 mil thickness, 9.5-inch cuff
- Exceptional strength and durability
- Superior puncture resistance
- Diamond textured finish for excellent grip
- Better chemical barriers than latex gloves
- Excellent tactile sensitivity and comfortable fit
- Dated Lot Codes for quality assurance and traceability

Handplus® Nitrile Manufacturing Standards

*\*Brand new state-of-the-art manufacturing plant with computer-controlled market leading technology*

| Defect                                    | Inspection Level | AQL |
|---|------------------|-----|
| Pinholes<br>(FDA 1000 ml watertight test) | G1               | 1.5 |
| Visual Defects (Major)                    | G1               | 2.5 |
| Visual Defects (Minor)                    | G1               | 4.0 |
| Dimensions                                | S-2              | 4.0 |

Handplus Nitrile XT8 ® Powder-Free Exam Gloves

| Size     | Reorder# |
|----------|----------|
| Small    | 088-6    |
| Medium   | 088-7    |
| Large    | 088-8    |
| X-Large  | 088-9    |
| XX-Large | 088-0    |

All specifications are subject to change without notice.

Specification (mm)

| Small    | Glove Length | Palm Width | Cuff Thickness | Palm Thickness | Finger Thickness |
|----------|--------------|------------|----------------|----------------|------------------|
| Small    | 245          | 85         | 0.12±0.01      | 0.17±0.01      | 0.20±0.01        |
| Medium   | 245          | 95         | 0.12±0.01      | 0.17±0.01      | 0.20±0.01        |
| Large    | 245          | 105        | 0.12±0.01      | 0.17±0.01      | 0.20±0.01        |
| X-Large  | 245          | 115        | 0.12±0.01      | 0.17±0.01      | 0.20±0.01        |
| 2X-Large | 245          | 125        | 0.12±0.01      | 0.17±0.01      | 0.20±0.01        |

Quality Standards

Testing Methods

- ASTM D 6319
- Food Safe Compliance FDA 21 CFR 177.2600
- ISO 9001:2008, ISO 13485:2003
- Tested for use in Food Service

Physical Properties

| Property       | ASTM Minimum | Handplus® Nitrile |
|----------------|--------------|-------------------|
|                | Before Aging | Before Aging      |
| Tensile (MPa)  | 14           | 14                |
| Elongation (%) | 500          | 500               |
|                | After Aging  | After Aging       |
| Tensile (MPa)  | 14           | 14                |
| Elongation (%) | 400          | 400               |