

SureGrip® Textured Powder-Free Latex Exam Gloves

Size	Reorder#
X-Small	035-5
Small	035-6
Medium	035-7
Large	035-8
X-Large	035-9
2X-Large	035-0

All specifications are subject to change without notice.

Specification (mm)

Size	Glove Length	Palm Width	Cuff Thickness	Palm Thickness	Finger Thickness
X-Small	240	75	0.11 ± 0.01	0.16 ± 0.01	0.18 ± 0.01
Small	240	85	0.11 ± 0.01	0.16 ± 0.01	0.18 ± 0.01
Medium	240	95	0.11 ± 0.01	0.16 ± 0.01	0.18 ± 0.01
Large	240	105	0.11 ± 0.01	0.16 ± 0.01	0.18 ± 0.01
X-Large	240	115	0.11 ± 0.01	0.16 ± 0.01	0.18 ± 0.01
2X-Large	240	120	0.11 ± 0.01	0.16 ± 0.01	0.18 ± 0.01

Quality Standards

Testing Methods

- Meets or exceeds the following standards: ASTM3578, D3578, D5151, D3767, D412, D6124, EN 455 (1&2), AS 40 (Australia), FDA, CE
- Quality sampled in accordance with MIL STD 105E
- ISO 9001 Certified Manufacturing
- Meets the Viral Penetration Test (ASTM F1671)

Physical Properties

Property	ASTM Minimum	SureGrip®
	Before Aging	Before Aging
Tensile (MPa)	18	21
Elongation (%)	650	750
	After Aging	After Aging
Tensile (MPa)	14	16
Elongation (%)	500	600

Features

Safety Sealed Packaging (XS-XXL)
100 Gloves/Box (XS-L), 90 Gloves/Box (XL-XXL)
10 Boxes/Case

- Textured finish
- Natural Color
- Minimum 7 mil thickness for better protection against punctures, rips and certain chemicals
- Excellent tactile sensitivity and comfortable fit
- Superior strength and durability
- Low modulus compound for maximum softness and comfort
- Dated Lot Codes for quality assurance and traceability

SureGrip® Manufacturing Standards

***Brand new state-of-the-art manufacturing plant with computer-controlled market leading technology**

Defect	Inspection Level	AQL
Pinholes (FDA 1000 ml watertight test)	G1	1.5
Visual Defects (Major)	G1	2.5
Visual Defects (Minor)	G1	4.0
Dimensions	S-2	4.0