



## Features

**Safety Sealed Packaging**  
**(S-XL) 100 Gloves/Box, 10 Boxes/Case**  
**(XXL) 90 Gloves/Box, 10 Boxes/Case**

- 100% Nitrile
- Blue Color
- 6 mil thickness for better protection against punctures, rips and certain chemicals
- Excellent tactile sensitivity and comfortable fit
- Superior strength and durability
- Tested for use with Chemotherapy Drugs per ASTM D6978
- Dated Lot Codes for quality assurance and traceability

## UniPro® Permeation Testing Results with Chemotherapy Drugs per ASTM D6978

Test Chemical	Breakthrough Detection Time (Min)
Cisplatin 1,000 ppm	No breakthrough was detected up to 240 minutes
Cyclophosphamide 20,000 ppm	No breakthrough was detected up to 240 minutes
Dacarbazine 10,000 ppm	No breakthrough was detected up to 240 minutes
Doxorubicin Hydrochloride 2,000 ppm	No breakthrough was detected up to 240 minutes
Etoposide 20,000 ppm	No breakthrough was detected up to 240 minutes
5-Fluorouracil 50,000 ppm	No breakthrough was detected up to 240 minutes
Paclitaxel (Taxol) 6,000 ppm	No breakthrough was detected up to 240 minutes
Thio-Tepa 10,000 ppm	Not Recommended
Carmustine 3,300 ppm	Not Recommended

## UniPro® Textured Powder-Free Nitrile Exam Gloves

Size	Reorder#
Small	702-6
Medium	702-7
Large	702-8
X-Large	702-9
2X-Large	702-0

*All specifications are subject to change without notice.*

## Specification (mm)

Size	Glove Length	Palm Width	Cuff Thickness	Palm Thickness	Finger Thickness
Small	242	75	0.10 ± 0.01	0.12 ± 0.01	0.16 ± 0.01
Medium	242	85	0.10 ± 0.01	0.12 ± 0.01	0.16 ± 0.01
Large	242	95	0.10 ± 0.01	0.12 ± 0.01	0.16 ± 0.01
X-Large	242	105	0.10 ± 0.01	0.12 ± 0.01	0.16 ± 0.01
2X-Large	242	115	0.10 ± 0.01	0.12 ± 0.01	0.16 ± 0.01

## Quality Standards

### Testing Methods

- Meets or exceeds the following standards: ASTM D6319, AQL 1.5, EN 455 (1&2), AS 40 (Australia), FDA, CE
- Quality sampled in accordance with MIL STD 105E
- ISO 9001 Certified Manufacturing
- Meets the Viral Penetration Test (ASTM F1671)

## Physical Properties

Property	ASTM Minimum	UniPro®
	Before Aging	Before Aging
Tensile (MPa)	18	21
Elongation (%)	500	590
	After Aging	After Aging
Tensile (MPa)	14	21
Elongation (%)	400	500