## UNISEAL SOLUTIONS AT HAND



### Features

#### Safety Sealed Packaging (S-XL) 100 Gloves/Box, 10 Boxes/Case

- 6 mil thickness, 9" cuff
- Textured for better grip
- Low protein count finish
- Excellent wet and dry grip
- Superior strength and durability
- Low modulus compound for maximum softness and comfort
- Dated Lot Codes for quality assurance and traceability

## **Manufacturing Standards**

Brand new state of the art manufacturing plant with computer-controlled market leading technology

Defect	Inspection Level	AQL
Pinholes (FDA 1000ml,watertight test)	G-1	1.5
Visual Defects (major)	G-1	2.5
Visual Defects (minor)	G-1	4.0
Dimensions	S-2	4.0

# **TECHNICAL DATA SHEET**

BLACKSEAL <sup>®</sup> Premium Latex Exam Gloves		
Size	Reorder#	
Small	888-6	
Medium	888-7	
Large	888-8	
X-Large	888-9	

All specifications are subject to change without notice.

Specification (mm)					
Size	Glove Length	Palm Width	Cuff Thickness	Palm Thickness	Finger Thickness
Small	240	85	$0.11 \pm 0.01$	$0.14 \pm 0.01$	$0.16 \pm 0.01$
Medium	240	95	$0.11 \pm 0.01$	$0.14 \pm 0.01$	$0.16 \pm 0.01$
Large	240	105	$0.11 \pm 0.01$	$0.14 \pm 0.01$	$0.16 \pm 0.01$
X-Large	240	115	$0.11 \pm 0.01$	$0.14 \pm 0.01$	$0.16 \pm 0.01$

## **Quality Standards**

#### **Testing Methods**

- Meets or exceeds the following standards: ASTM D3578, EN 455 (EE), AS 40 (Australia), FDA, CE
- Quality sampled in accordance with MIL STD 105D
- Meets the Viral Penetration Test (ASTM FI671)
- Passes 200 Human Modified Draize Skin Allergy Test

## **Physical Properties**

ASTM Minimum	UniSeal <sup>®</sup> Blackseal	
Before Aging	Before Aging	
18	21	
500	700	
After Aging	After Aging	
14	16	
400	500	
	Before Aging 18 500 After Aging 14	